

Short description of Material:

A partially crystalline high performance plastic with specifically improved sliding and through the addition of a solid lubricant. The excellent properties of pure PEEK are not affected.

Application examples:

- gears
- bushings
- piston rings
- valves
- wiper blades

Colours: black

Mechanical values

		dry	
Density	ISO 1183	1,48	g/cm ³
Yield stress	ISO 527	118	MPa
Elongation due to tearing	ISO 527	3	%
Modulus of elasticity resulting from tensile test	ISO 527	8.100	MPa
Modulus of elasticity resulting from bending test	ISO 178	10.000	MPa
Flexural strength	ISO 178	210	MPa
Impact strength ¹⁾	ISO 179	25	kJ/m ²
Notched-bar impact strength	ISO 179	2,5	kJ/m ²
Ball indentation hardness H _{358/30}	ISO 2039-1	270	MPa
Creep rate stress at 1% elongation ²⁾	DIN 53 444	-	MPa
Sliding friction coefficient against steel (dry running) ³⁾	—	0,11	—
Sliding wear against steel (dry running) ³⁾	—	-	µm/km

Thermal values

Melting temperature	ISO 3146	+ 340	°C
Thermal conductivity	DIN 52 612	0,24	W/(K·m)
Specific thermal capacity	—	-	J/(g·K)
Coefficient of linear expansion ⁴⁾	—	3	10 ⁻⁵ ·K ⁻¹
Operating temperature range (long-term) ⁵⁾	—	- 40 / + 250	°C
Operating temperature range (short-term) ⁵⁾	—	+ 310	°C
Fire behaviour	UL 94	V - 0	—

Electrical values

Dielectric constant ⁶⁾	IEC 250	-	—
Dielectric loss factor ⁶⁾	IEC 250	10 ⁵	—
Specific volume resistance	IEC 93	-	Ω·cm
Surface resistance	IEC 93	-	Ω
Dielectric strength	IEC 243	24,5	KV/mm
Creep current resistance	IEC 112	-	—

Miscellaneous data

Moisture absorption in normal climate until saturated	DIN 53 715	0,14	%
Water absorption until saturated	ISO 62	0,3	%

¹⁾: Measured with a pendulum impact testing machine 0,1 DIN 51 222

²⁾: Tension resulting in 1% total elongation after 1.000 h

³⁾: against steel, hardened and ground, P = 0,05 MPa, V = 0,6 m/s, t = 60 °C near running surface

⁴⁾: For a temperature range of + 23 °C to + 60 °C

⁵⁾: Experience values established with finished parts that are not under any stress in heated air, depending on the type and form of heat exposure, short-term = max. 1 h, long-term = months

⁶⁾: at 10⁶ Hz

w.b. = without breakage
 1 MPa = 1 N/mm²
 1 g/cm³ = 1.000 kg/m³
 1 kV/mm = 1 MV/m

Licharz GmbH

Industriepark Nord 15

D - 53567 Buchholz/Germany

Phone: ++49 / (0) 26 83 / 9 77 -0

Fax: ++49 / (0) 26 83 / 9 77 -111

Internet: www.licharz.de

E-Mail: info@licharz.de